

LNM 309LSi

CLASSIFICATION

AWS A5.9	ER309LSi	A-Nr	8	Mat-Nr	1.4332
ISO 14343-A	G 23 12 LSi	F-Nr	6		
		9606 FM	5		

GENERAL DESCRIPTION

Solid wire for welding stainless steel to carbon steel
With high silicon for improved wettability

WELDING POSITIONS (ISO/ASME)



PA/1G



PB/2F



PC/2G



PD/4F



PE/4G



PF/3Gu

SHIELDING GASES (ACC. ISO 14175)

M12	Mixed gas Ar+ 0.5-5% CO ₂
M13	Mixed gas Ar+ 0.5-3% O ₂

APPROVALS

ABS	BV	DB	DNV	GL	LR	TÜV
+	+	+	+	+	+	+

CHEMICAL COMPOSITION (W%) TYPICAL WIRE

C	Mn	Si	Cr	Ni	Mo
0.02	1.8	0.8	23.3	13.8	0.14

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Shielding gas	Condition	0.2% proof strength	Tensile strength	Elongation	Impact ISO-V(J)	
			[N/mm ²]	[N/mm ²]	[%]	-20°C	+20°C
Typical values	M12	AW	436	582	37	80	87

EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	EN 10088-1/-2	Mat. Nr	ASTM	UNS
Corrosion resistant cladsteels				
	X2CrNi18-10	1.4311	(TP)304LN	S30453
	X2CrNi19-11	1.4306	(TP)304L	S30403
			CF-3	J92500
	X4CrNi18-10	1.4301	(TP)304	S30400

Dissimilar metals (mild and low alloy steel to stainless steel)
Build-up welding on mild and low alloy steel

PACKAGING AND AVAILABLE SIZES

Diameter [mm]	0.8	1.0	1.2	1.6
15 kg spool BS300	X	X	X	X
250 kg Accutrak® Drum		X	X	

Other sizes and packaging on request

LNM 309LSi: rev. C-EN22-01/02/16