

Arosta® 309S

EMR
SAHARA®

CLASSIFICATION

AWS A5.4	E309L-16	A-Nr	8	Mat-Nr	1.4332
ISO 3581-A	E 23 12 L R 3 2	F-Nr	5		
		9606 FM	5		

TEMPERATURE RANGE

Pressurized parts : -120...+300°C
Oxidation resistance : n.a

GENERAL DESCRIPTION

A rutile-basic high CrNi alloyed buffer electrode
For welding stainless steel to mild steel and root runs in clad steel
Applicable for root passes in N alloyed AISI 304LN steels
Excellent weldability and self releasing slag
High resistance to embrittlement
Weldable on AC and DC+ polarity
Also available in vacuum sealed Sahara ReadyPack® (SRP)

WELDING POSITIONS (ISO/ASME)



PA/1G



PB/2F



PC/2G



PF/3Gu



PE/4G



PH/5Gu

CURRENT TYPE

AC/DC +

APPROVALS

ABS	BV	RMRS	TÜV
+	309L	SS/CMn	+

CHEMICAL COMPOSITION (W%), TYPICAL, ALL WELD METAL

C	Mn	Si	Cr	Ni	FN (acc.WRC 1992)
0.02	0.8	0.8	23.5	12.5	12-20

MECHANICAL PROPERTIES, TYPICAL, ALL WELD METAL

	Condition	0.2% Proof strength (N/mm²)	Tensile strength (N/mm²)	Elongation (%)	Impact ISO-V(J)		
					+20°C	-20°C	-120°C
Required: AWS A5.4 ISO 3581-A Typical values	AW	not required min. 320 480	min. 520 min. 510 560	min. 30 min. 25 40	not required not required 60	50	40

PACKAGING AND AVAILABLE SIZES

	Diameter (mm) Length (mm)	2.5	3.2	4.0	5.0
		350	350	350	350
Carton + PE foil	Pieces / unit	135	150	100	65
	Net weight/unit (kg)	2.8	5.0	5.0	5.0
SRP	Pieces / unit	69	56	-	-
	Net weight/unit (kg)	1.4	1.9	-	-

Identification Imprint: 309L-16 / AROSTA 309 S Tip Color: sea green

Arosta®309S: rev. C-EN25-01/02/16

Arosta® 309S

EXAMPLES OF MATERIALS TO BE WELDED

Steel grades	EN 10088-1/-2	Mat. Nr	ASTM/ACI A240/A312/A351	UNS
Corrosion resistant cladsteels				
	X2CrNi18-10	1.4311	(TP)304LN	S30453
	X2CrNi19-11	1.4306	(TP)304L	S30403
			CF-3	J92500
	X4CrNi18-10	1.4301	(TP)304	S30400

Dissimilar metals (mild and low alloy steel to CrNi or CrNiMo stainless steel)

Build-up welding on mild and low alloy steel

Bufferlayer CrNi-cladsteel

CALCULATION DATA

Sizes Diam. x length (mm)	Current range (A)	Current type	Arc time - per electrode at max. current - (s)*	Energy E(kJ)	Dep. rate H(kg/h)	Weight/ 1000 pcs (kg)	Electrodes/ kg weldmetal B	kg electrodes/ kg weldmetal 1/N
2.5 x 350	40 - 75	DC+	50	88	0.93	21.0	77	1.61
3.2 x 350	60 - 110	DC+	58	160	1.3	32.5	46	1.49
4.0 x 350	80 - 150	DC+	64	241	1.8	48.3	31	1.49
5.0 x 350	140 - 220	DC+	68	372	2.8	78.0	19	1.49

*Stub end 35mm

WELDING PARAMETERS, OPTIMUM FILL PASSES

Diameter (mm)	Welding positions					
	PA/1G	PB/2F	PC/2G	PF/3Gup	PE/4G	PH/5Gup
2.5	70A	70A	70A	60A	60A	60A
3.2	100A	100A	100A	70A	70A	70A
4.0	140A	140A	140A	80A		
5.0	180A	180A	180A			